



Heidelberg Materials UK
Second Floor, Arena Court, Crown Lane
Maidenhead, Berkshire, SL6 8QZ
Padeswood Works
1333-CPR-00121




Cement Test Report

Heidelberg Materials UK
Ketton
Stamford
PE9 3SX
Tel: 0330 123 2074
Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of
Padeswood PC, BS EN 197-1:2011 - CEM I 52,5N
Dispatched from Padeswood during week ending 29-Sep-24 (Week No. 2024-39)
and during week ending 08-Sep-24 (Week No. 2024-36) for 28 day results

Date	Fineness	Setting Time	Soundness	Compressive Strength			Chloride	Alkali	
	Specific Surface (m ² /kg)	Initial (mins)	Expansion (mm)	40mm x 40mm x 160mm Mortar prisms			%	Certified Average Alkali % Na ₂ O eq	Standard Deviation
				2 Days (N/mm ²)	7 Days (N/mm ²)	28 Days (N/mm ²)			
23-Sep-24	440	200	0	29.0	45.5		0.03	0.50	0.02
24-Sep-24	435	180		30.5	47.0		0.03	0.50	0.02
26-Sep-24	435	190		31.0	50.0		0.03	0.50	0.02
27-Sep-24	440	185		26.0	44.5		0.03	0.50	0.02
Average	440	190		29.0	47.0		0.03		0.02
02-Sep-24	435	145	0	29.0	47.0	57.0	0.03	0.51	0.02
03-Sep-24	435	145		31.0	48.5	58.0	0.03	0.51	0.02
04-Sep-24	435	170		30.0	46.5	58.0	0.03	0.51	0.02
06-Sep-24	445	145		29.5	46.0	58.0	0.03	0.51	0.02
Average	440	150		30.0	47.0	58.0	0.03		0.02

Product Declaration:
Declared Mean Alkali (%) = 0.75 (Max)
Declared Chloride content (%) = 0.07 (Max)

For and on behalf of
HEIDELBERG MATERIALS UK

Dr Nina Cardinal, Dipl.Ing., CEng, MICT
National Technical Manager
Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.