

Certificate of Conformity Summary



Purfleet - February 2025

Combinations of evoBuild Low Carbon GGBS supplied from Heidelberg Materials UK in combination with the CEM I Portland Cements and CEM II Portland Limestone Cements (PLC) listed below conform with the requirements of BS 8500-2:2023 over the indicated range of proportions. The compressive strength results are for tests carried out in accordance with BS EN 197-1 with 50% evoBuild Low Carbon GGBS in combination with the indicated cement. The combination of cement sources in bold text have been evaluated for conformity for less than six months.

In order to establish the designation of the combination as per Table 1 of BS 8500-2:2023, the user requires to know the limestone content of the cement. For cements supplied by Heidelberg Materials UK, this is shown in brackets in the table below. For cements of other sources the user should refer to the supplier for this information.

Composite samples for Heidelberg Materials UK cements and evoBuild Low Carbon GGBS are obtained by blending not less than 8 spot samples of similar mass, taken at regular intervals throughout the relevant period. For information on composite samples of other cement sources, the user should refer to the supplier.

Cement Source		Compressive Strength N/mm2		evoBuild Low Carbon GGBS Percentage Range					
				42.5L 32.5L			22.5		
Source	7 day	28 day	Min	Max	Min	Max	Min	Max	
ABERTHAW	28.8	53.8	16	65	44	80	74	88	
CHATHAM	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a	
RUGBY PLC	31.5	52.1	6	61	51	73	68	82	
TILBURY PLC	31.8	54.5	6	60	45	74	68	83	
SILIFKE	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a	
NEWPORT-PLATIN	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a	
CAULDON PLC	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a	
KETTON (3-5%)	30.2	53.9	6	59	49	73	67	83	
MACEIRA-LIZ	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a	
CAULDON 52.5N	32.5	54.3	10	68	45	79	75	87	
PADESWOOD (3-5%)	33.5	55.3	6	67	50	80	75	89	
TUNSTEAD	26.1	50.9	8	57	47	71	65	84	
RIBBLESDALE (3-5%)	31.1	55.3	6	63	46	77	72	86	
RUGBY	31.1	51.7	6	59	45	75	69	85	
LEMONA	31.1	54.2	9	58	47	73	66	83	
CHATHAM LAGERDORF	33.3	55.5	10	63	54	76	70	85	
PLATIN	29.7	53.5	6	65	47	80	74	90	
TILBURY	30.6	52.9	6	56	43	75	68	86	
ALHANDRA 52.5R	30.6	55.8	22	64	50	78	72	88	
MANNOK	35.1	58.1	6	63	54	77	70	87	
HOPE	29.4	55.8	6	61	49	76	70	87	
LIMERICK	29.6	50.9	6	58	23	73	67	83	
METAPORQUERA	31.0	55.8	6	66	52	77	72	85	
KETTON PLC (9-13%)	34.6	57.0	6	60	50	73	67	82	
PADESWOOD PLC (8-12%)	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a	
ABONO	34.6	57.5	6	64	55	80	73	80	
GHENT	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a	
HOPE PLC	35.3	54.9	17	61	48	76	70	87	
SEVILLE	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a	
	Source ABERTHAW CHATHAM RUGBY PLC TILBURY PLC SILIFKE NEWPORT-PLATIN CAULDON PLC KETTON (3-5%) MACEIRA-LIZ CAULDON 52.5N PADESWOOD (3-5%) TUNSTEAD RIBBLESDALE (3-5%) RUGBY LEMONA CHATHAM LAGERDORF PLATIN TILBURY ALHANDRA 52.5R MANNOK HOPE LIMERICK METAPORQUERA KETTON PLC (9-13%) PADESWOOD PLC (8-12%) ABONO GHENT HOPE PLC	Source	Source Strength N/mm2 Source 7 day 28 day ABERTHAW 28.8 53.8 CHATHAM No Sample RUGBY PLC 31.5 52.1 TILBURY PLC 31.8 54.5 SILIFKE No Sample NEWPORT-PLATIN No Sample CAULDON PLC No Sample KETTON (3-5%) 30.2 53.9 MACEIRA-LIZ No Sample CAULDON 52.5N 32.5 54.3 PADESWOOD (3-5%) 33.5 55.3 TUNSTEAD 26.1 50.9 RIBBLESDALE (3-5%) 31.1 55.3 RUGBY 31.1 51.7 LEMONA 31.1 54.2 CHATHAM LAGERDORF 33.3 55.5 PLATIN 29.7 53.5 TILBURY 30.6 52.9 ALHANDRA 52.5R 30.6 55.8 MANNOK 35.1 58.1 HOPE 29.4	Source	Source	Source	Source	Source Strength N/mm2 42.5L 32.5L 22 32 32 32 32 33 34 34	

The evoBuildLow Carbon GGBS contained no additional materials others than those permitted according to BS EN 15167-1.

Heidelber Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.

Signed:

Dr Nina Cardinal, Dipl.Ing., CEng, MICT. Technical Strategy Director