

Port Talbot - January 2025

Combinations of evoBuild Low Carbon GGBS supplied from Heidelberg Materials UK in combination with the CEM I Portland Cements and CEM II Portland Limestone Cements (PLC) listed below conform with the requirements of BS 8500-2:2023 over the indicated range of proportions. The compressive strength results are for tests carried out in accordance with BS EN 197-1 with 50% evoBuild Low Carbon GGBS in combination with the indicated cement. The combination of cement sources in bold text have been evaluated for conformity for less than six months.

In order to establish the designation of the combination as per Table 1 of BS 8500-2:2023, the user requires to know the limestone content of the cement. For cements supplied by Heidelberg Materials UK, this is shown in brackets in the table below. For cements of other sources the user should refer to the supplier for this information.

Composite samples for Heidelberg Materials UK cements and evoBuild Low Carbon GGBS are obtained by blending not less than 8 spot samples of similar mass, taken at regular intervals throughout the relevant period. For information on composite samples of other cement sources, the user should refer to the supplier.

Cement Source		Compressive Strength N/mm2		evoBuild Low Carbon GGBS Percentage Range					
Company	Source	7 day	28 day	42.5L		32.5L		22.5	
				Min	Max	Min	Max	Min	Max
HEIDELBERG MATERIALS	PADESWOOD (3-5%)	30.1	52.6	6	59	46	73	67	83
LAFARGE	OGGAZ	30.6	53.4	12	66	56	77	72	86
TARMAC	ABERTHAW	30.2	50.5	6	65	41	80	74	89
DRAGON ALFA	METAPORQUERA PLC	32.2	51.4	6	65	52	78	72	86
TARMAC	ABERTHAW PLC	29.5	49.1	6	58	44	73	66	85
CEMEX	RUGBY PLC	30.5	52.9	6	67	55	78	73	87
CEMEX	TILBURY PLC	32.5	52.4	6	61	42	76	70	86
CEMEX	NEWPORT-PLATIN	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
LAFARGE	CAULDON PLC	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
HEIDELBERG MATERIALS	KETTON (3-5%)	29.8	48.3	6	62	48	77	71	88
LAFARGE	CAULDON 52.5N	28.9	53.9	11	62	45	79	73	89
TARMAC	TUNSTEAD	29.5	54.0	9	68	50	80	75	88
HEIDELBERG MATERIALS	RIBBLESDALE (3-5%)	29.1	48.8	6	57	47	72	65	87
CEMEX	RUGBY	28.0	49.1	6	59	45	76	69	86
SOUTHERN-PREMIER	LEMONA	30.3	52.5	6	64	49	80	74	90
TARMAC	DUNBAR	23.0	48.2	6	50	45	75	66	80
LAFARGE	CHATHAM LAGERDORF	30.9	51.8	6	68	54	80	75	90
SOUTHERN-PREMIER	PLATIN	29.1	49.8	6	70	47	83	77	80
CEMEX	TILBURY	30.4	50.5	6	58	43	76	69	86
LAFARGE	COOKSTOWN	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
CIMPOR	ALHANDRA 52.5R	30.7	53.6	6	63	54	76	70	85
BREEDON	HOPE	30.0	52.4	6	61	49	77	70	89
SOUTHERN-PREMIER	LIMERICK	28.4	48.3	6	59	47	73	66	85
DRAGON ALFA	METAPORQUERA	30.6	52.7	6	63	52	75	70	83
VICAT	ST. EGREVE	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
CEMEX (LEITH)	ALCANAR	27.9	53.2	15	58	48	77	69	90
TILlicouLTRY	LAGAN	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
HEIDELBERG MATERIALS	KETTON PLC (9-13%)	33.1	51.0	6	60	50	72	66	82
HEIDELBERG MATERIALS	PADESWOOD PLC (8-12%)	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
PREMIER CEMENT	CEMENTOS MOLINS	No	Sample	n/a	n/a	n/a	n/a	n/a	n/a
BREEDON	HOPE PLC	31.9	53.7	6	62	49	77	70	87

The evoBuildLow Carbon GGBS contained no additional materials others than those permitted according to BS EN 15167-1.

Heidelber Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.

Signed:



Dr Nina Cardinal, Dipl.Ing., CEng, MICT. Technical Strategy Director