



Heidelberg Materials UK
Second Floor, Arena Court, Crown Lane
Maidenhead, Berkshire, SL6 8QZ
Ketton Works
1333-CPR-00254



Cement Test Report

Heidelberg Materials UK
Ketton
Stamford
PE9 3SX
Tel: 0330 123 2074
Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of
Ketton PLC 52,5N, BS EN 197-1:2011 - CEM II/A-LL 52,5N

Dispatched from Ketton during week ending
and during week ending

17-Aug-25 (Week No. 2025-32)
27-Jul-25 (Week No. 2025-29) for 28 day results

Date	Fineness	Setting Time	Soundness	Compressive Strength			Chloride	Alkali	
	Specific Surface (m²/kg)	Initial (mins)	Expansion (mm)	40mm x 40mm x 160mm Mortar prisms			%	Certified Average Alkali % Na₂O eq	Standard Deviation
				2 Days (N/mm²)	7 Days (N/mm²)	28 Days (N/mm²)			
11-Aug-25	495	140	0	33.0	51.5		0.04	0.67	0.04
13-Aug-25	510	150		35.0	54.0		0.04	0.66	0.05
Average	505	145		34.0	53.0		0.04		0.04
21-Jul-25	520	165	0	35.5	50.5	62.5	0.04	0.68	0.01
23-Jul-25	510	155		38.0	50.0	61.5	0.04	0.68	0.02
Average	515	160		37.0	50.5	62.0	0.04		0.02

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Chloride content (%) = 0.07 (Max)

For and on behalf of
HEIDELBERG MATERIALS UK


Dr Nina Cardinal, Dipl.Ing., CEng, MICT
Technical Strategy Director
Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.