



Heidelberg Materials UK  
Second Floor, Arena Court, Crown Lane  
Maidenhead, Berkshire, SL6 8QZ  
Ketton Works  
1333-CPR-00254



## Cement Test Report

Heidelberg Materials UK  
Ketton  
Stamford  
PE9 3SX  
Tel: 0330 123 2074  
Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of  
Ketton PLC 52,5N, BS EN 197-1:2011 - CEM II/A-LL 52,5N

Dispatched from Ketton during week ending  
and during week ending

16-Nov-25 (Week No. 2025-45 )  
26-Oct-25 (Week No. 2025-42 ) for 28 day results

| Date      | Fineness                    | Setting Time      | Soundness         | Compressive Strength              |                   |                    | Chloride | Alkali                                   |                       |
|-----------|-----------------------------|-------------------|-------------------|-----------------------------------|-------------------|--------------------|----------|------------------------------------------|-----------------------|
|           | Specific Surface<br>(m²/kg) | Initial<br>(mins) | Expansion<br>(mm) | 40mm x 40mm x 160mm Mortar prisms |                   |                    | %        | Certified<br>Average Alkali<br>% Na₂O eq | Standard<br>Deviation |
|           |                             |                   |                   | 2 Days<br>(N/mm²)                 | 7 Days<br>(N/mm²) | 28 Days<br>(N/mm²) |          |                                          |                       |
| 10-Nov-25 | 505                         | 170               | 1                 | 37.0                              | 53.5              |                    | 0.04     | 0.63                                     | 0.03                  |
| 12-Nov-25 | 510                         | 175               |                   | 35.5                              | 49.5              |                    | 0.04     | 0.62                                     | 0.03                  |
|           |                             |                   |                   |                                   |                   |                    |          |                                          |                       |
| Average   | 510                         | 175               | 1                 | 36.5                              | 51.5              |                    | 0.04     |                                          | 0.03                  |
| 20-Oct-25 | 510                         | 170               | 0                 | 35.0                              | 50.0              | 60.0               | 0.04     | 0.63                                     | 0.05                  |
| 22-Oct-25 | 500                         | 175               |                   | 37.0                              | 52.0              | 63.0               | 0.04     | 0.62                                     | 0.05                  |
|           |                             |                   |                   |                                   |                   |                    |          |                                          |                       |
| Average   | 505                         | 175               |                   | 36.0                              | 51.0              | 61.5               | 0.04     |                                          | 0.05                  |

### Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Chloride content (%) = 0.07 (Max)

For and on behalf of  
HEIDELBERG MATERIALS UK

  
Dr Nina Cardinal, Dipl.Ing., CEng, MICT  
Technical Strategy Director  
Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.