

## Cement Test Report

Heidelberg Materials UK  
Ketton  
Stamford  
PE9 3SX  
Tel: 0330 123 2074  
Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of  
Padeswood PLC 52,5N, BS EN 197-1:2011 - CEM II/A-LL 52,5N

Dispatched from Padeswood during week ending 16-Nov-25 (Week No. 2025-45 )  
and during week ending 26-Oct-25 (Week No. 2025-42 ) for 28 day results

Date	Fineness	Setting Time	Soundness	Compressive Strength			Chloride	Alkali	
	Specific Surface (m <sup>2</sup> /kg)	Initial (mins)	Expansion (mm)	40mm x 40mm x 160mm Mortar prisms			%	Certified Average Alkali % Na <sub>2</sub> O eq	Standard Deviation
				2 Days (N/mm <sup>2</sup> )	7 Days (N/mm <sup>2</sup> )	28 Days (N/mm <sup>2</sup> )			
Average									
23-Oct-25	450	185	1	31.5	52.0	61.0	0.04	0.44	0.03
Average	450		1	31.5	52.0	61.0	0.04		0.03

### Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Chloride content (%) = 0.07 (Max)

For and on behalf of  
HEIDELBERG MATERIALS UK

  
Dr Nina Cardinal, Dipl.Ing., CEng, MICT  
Technical Strategy Director  
Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.