



Heidelberg Materials UK
Second Floor, Arena Court, Crown Lane
Maidenhead, Berkshire, SL6 8QZ
Ribblesdale Works
1333-CPR-00127



Cement Test Report

Heidelberg Materials UK
Ketton
Stamford
PE9 3SX
Tel: 0330 123 2074
Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of
Ribblesdale PC, BS EN 197-1:2011 - CEM I 52,5N

Dispatched from Ribblesdale during week ending
and during week ending

11-Jan-26 (Week No. 2026-1)
21-Dec-25 (Week No. 2025-50) for 28 day results

Date	Fineness	Setting Time	Soundness	Compressive Strength			Chloride	Alkali	
	Specific Surface (m²/kg)	Initial (mins)	Expansion (mm)	40mm x 40mm x 160mm Mortar prisms			%	Certified Average Alkali % Na₂O eq	Standard Deviation
				2 Days (N/mm²)	7 Days (N/mm²)	28 Days (N/mm²)			
05-Jan-26	385	130	1	38.0	50.5		0.07	0.66	0.03
06-Jan-26	400	130		38.0	49.0		0.06	0.66	0.03
07-Jan-26	405	130		37.5	49.5		0.06	0.66	0.03
08-Jan-26	405	135		38.0	48.0		0.06	0.66	0.03
09-Jan-26	385	125		38.5	49.5		0.06	0.66	0.03
Average	395	130		38.0	49.5		0.06		0.03
15-Dec-25	395	125	1	37.5	48.5	58.0	0.07	0.66	0.03
16-Dec-25	400	145		38.0	49.0	60.5	0.07	0.66	0.03
17-Dec-25	400	145		38.0	48.5	60.0	0.07	0.66	0.03
18-Dec-25	405	135		38.5	48.0	59.0	0.07	0.66	0.03
19-Dec-25	410	120		37.0	49.0	59.5	0.07	0.66	0.03
Average	400	135		38.0	48.5	59.5	0.07		0.03

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Chloride content (%) = 0.07 (Max)

For and on behalf of
HEIDELBERG MATERIALS UK


Dr Nina Cardinal, Dipl.Ing., CEng, MICT
Technical Strategy Director
Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.