



1333

Heidelberg Materials UK
 Second Floor, Arena Court, Crown Lane
 Maidenhead, Berkshire, SL6 8QZ
 Ketton Works
 1333-CPR-00254



Cement Test Report

Heidelberg Materials
 UK
 Ketton
 Stamford
 PE9 3SX
 Tel: 0330 123 2074
 Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of
 Ketton PLC 52,5N, BS EN 197-1:2011 - CEM II/A-LL 52,5N

Dispatched from Ketton during week ending
 and during week ending

12-Apr-26 (Week No. 2026-14)
 22-Mar-26 (Week No. 2026-11) for 28 day results

Date	Fineness Specific Surface (m ² /kg)	Setting Time Initial (mins)	Soundness Expansion (mm)	Compressive Strength			Chloride mean of 25 %	Alkali	
				40mm x 40mm x 160mm Mortar prisms				Certified Average of 25 Alkali % Na ₂ O eq	Standard Deviation
				2 Days (N/mm ²)	7 Days (N/mm ²)	28 Days (N/mm ²)			
07-Apr-26	515	165	0	36.5	54.0		0.04	0.63	0.03
09-Apr-26	545	170		39.5	53.5		0.04	0.63	0.03
Average	530	170		38.0	54.0				
16-Mar-26	525	185	0	39.5	55.0	65.5	0.04	0.63	0.02
18-Mar-26	515	150		40.5	57.5	68.0	0.04	0.63	0.03
Average	520	170		40.0	56.5	67.0			

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Mean Chloride content (%) = 0.07 (Max)

For and on behalf of
 HEIDELBERG MATERIALS UK

Dr Nina Cardinal, Dipl.Ing., CEng, MICT
 Technical Strategy Director
 Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.