



1333

Heidelberg Materials UK  
 Second Floor, Arena Court, Crown Lane  
 Maidenhead, Berkshire, SL6 8QZ  
 Padeswood Works  
 1333-CPR-00121



## Cement Test Report

Heidelberg Materials  
 UK  
 Ketton  
 Stamford  
 PE9 3SX  
 Tel: 0330 123 2074  
 Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of

Padeswood PC, BS EN 197-1:2011 - CEM I 52,5N

Dispatched from Padeswood during week ending  
 and during week ending

19-Apr-26 (Week No. 2026-15 )

29-Mar-26 (Week No. 2026-12 ) for 28 day results

Date	Fineness Specific Surface (m <sup>2</sup> /kg)	Setting Time Initial (mins)	Soundness Expansion (mm)	Compressive Strength			Chloride mean of 25 %	Alkali	
				40mm x 40mm x 160mm Mortar prisms				Certified Average of 25 Alkali % Na <sub>2</sub> O eq	Standard Deviation
				2 Days (N/mm <sup>2</sup> )	7 Days (N/mm <sup>2</sup> )	28 Days (N/mm <sup>2</sup> )			
13-Apr-26	475	160	1	32.5	50.0		0.07	0.55	0.02
15-Apr-26	425	170		29.5	48.0		0.07	0.55	0.02
Average	450	165		31.0	49.0				
24-Mar-26	445	170	1	31.0	47.5	60.0	0.07	0.55	0.01
26-Mar-26	435	150		32.5	50.5	62.0	0.07	0.55	0.01
27-Mar-26	430	160		31.5	49.0	61.0	0.07	0.55	0.01
Average	435	160		31.5	49.0	61.0			

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Mean Chloride content (%) = 0.07 (Max)

For and on behalf of  
 HEIDELBERG MATERIALS UK

Dr Nina Cardinal, Dipl.Ing., CEng, MICT

Technical Strategy Director

Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.