

## Chemical Report

Heidelberg Materials  
UK  
Ketton  
Stamford  
PE9 3SX  
Tel: 0330 123 2074  
Fax: 01780 727008

Composition of Ketton PLC 52,5N, EN 197-1:2011, CEM II/A-LL 52,5N

Dispatched from Ketton

Chemical analysis for week ending 31-May-26


Week No. 2026-21

Compound	%
SiO <sub>2</sub>	19.73
Al <sub>2</sub> O <sub>3</sub>	4.81
Fe <sub>2</sub> O <sub>3</sub>	2.98
CaO	65.00
MgO	1.11
SO <sub>3</sub>	3.25
K <sub>2</sub> O	0.52
Na <sub>2</sub> O	0.30
Cl	0.05
Loss on Ignition	n/a
Not Detected	2.26
Total	97.74

	%
Insol Residue	n/a
Free CaO	0.1
Certified Average Alkali Na <sub>2</sub> O (Equiv)	0.61
LSF (x 100)	99.65

Clinker compounds by Rietveld analysis	
C <sub>3</sub> S	55.3
C <sub>2</sub> S	13.4
C <sub>3</sub> A	8.4
C <sub>4</sub> AF	7.7

For and on behalf of  
HEIDELBERG MATERIALS UK



Dr Nina Cardinal, Dipl.Ing., CEng, MICT  
Technical Strategy Director  
Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.