

**evoBuild Low Carbon GGBS Produced at:**  
**Sample Period:**

**Teesside**  
**April 2026**

**Certificate of Conformity of evoBuild Low Carbon GGBS**

Spot samples of evoBuild low carbon GGBS were taken and tested to determine conformity to the autocontrol requirements of EN 15167-1 "Ground granulated blastfurnace slag for use in concrete, mortar and grout" following the methods given in that standard. The values reported are mean values for the monthly production period.

	Result	EN Limit
<b>GGBS Only</b>		
Fineness m <sup>2</sup> /kg	450	min. 275
Magnesia MgO %	6	max. 18
Sulfate SO <sup>3</sup> %	0.29	max. 2.5
Sulfide S <sup>2-</sup> %	0.65	max. 2.0
Chloride Content Cl %	0.01	max. 0.1
Moisture Content %	0.11	max. 1.0
Alumina Al <sub>2</sub> O <sub>3</sub> %	15	

Note: If the value is ≥ 14% the '+SR' restriction will be exceeded if the C<sub>3</sub>A of the CEM I is > 10%.

<b>Alkalis as Na<sub>2</sub>O equ. (acid soluble)</b>		
Certified Average Alkali (Last 25) %	≤ 1.0	
Mean Alkali content (Last 25) %	0.36	
Declared Mean : Mean last 25 + (SD last 25 x 1.64) %	0.42	

<b>Combination of 50% Laboratory Stock CEM I Portland Cement and 50% evoBUILD Low Carbon GGBS</b>			
Initial Setting Time min.		239	> 2 x PC
Activity Index %	7 days	72	min. 45
	28 days	91	min. 70

<b>Laboratory Stock CEM I Portland Cement Only</b>			
<i>The laboratory stock CEM I Portland cement used in these tests was supplied by Heidelberg Materials UK.</i>			
Initial Setting Time min		161	
Compressive Strength N/mm <sup>2</sup>	7 days	47.5	
	28 days	59.9	

The evoBuild GGBS contained no additional materials other than those permitted. The above results and other tests demonstrate the conformity of the material sold during the month to the requirements of EN 15167-1.

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.

Signed:

Dr Nina Cardinal, Dipl.Ing., CEng, MICT. Technical Strategy Director

1333-CPR-00212