



1333

Heidelberg Materials UK  
 Second Floor, Arena Court, Crown Lane  
 Maidenhead, Berkshire, SL6 8QZ  
 Ketton Works  
 1333-CPR-00254



## Cement Test Report

Heidelberg Materials  
 UK  
 Ketton  
 Stamford  
 PE9 3SX  
 Tel: 0330 123 2074  
 Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of  
 Ketton PLC 52,5N, BS EN 197-1:2011 - CEM II/A-LL 52,5N

Dispatched from Ketton during week ending  
 and during week ending

14-Jun-26 (Week No. 2026-23 )  
 24-May-26 (Week No. 2026-20 ) for 28 day results

Date	Fineness	Setting Time	Soundness	Compressive Strength			Chloride	Alkali		
				40mm x 40mm x 160mm Mortar prisms				mean of 25 %	Certified Average of 25 Alkali % Na <sub>2</sub> O eq	Standard Deviation
				2 Days (N/mm <sup>2</sup> )	7 Days (N/mm <sup>2</sup> )	28 Days (N/mm <sup>2</sup> )				
08-Jun-26	540	145	0	38.0	52.5		0.04	0.61	0.03	
10-Jun-26	535	175		36.0	52.0					
Average	540	160		37.0	52.5					
18-May-26	525	150	1	38.5	53.0	62.0	0.04	0.61	0.03	
20-May-26	510	150		37.5	54.0	62.5				
Average	520	150		38.0	53.5	62.5				

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Mean Chloride content (%) = 0.07 (Max)

For and on behalf of  
 HEIDELBERG MATERIALS UK

Dr Nina Cardinal, Dipl.Ing., CEng, MICT  
 Technical Strategy Director  
 Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.