



1333

Heidelberg Materials UK
 Second Floor, Arena Court, Crown Lane
 Maidenhead, Berkshire, SL6 8QZ
 Ketton Works
 1333-CPR-00122



Cement Test Report

Heidelberg Materials
 UK
 Ketton
 Stamford
 PE9 3SX
 Tel: 0330 123 2074
 Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of

Ketton PC, BS EN 197-1:2011 - CEM I 52,5N

Dispatched from Ketton during week ending

21-Jun-26 (Week No. 2026-24)

and during week ending

31-May-26 (Week No. 2026-21) for 28 day results

Date	Fineness	Setting Time	Soundness	Compressive Strength			Chloride	Alkali					
				Specific Surface (m ² /kg)	Initial (mins)	Expansion (mm)		40mm x 40mm x 160mm Mortar prisms			mean of 25 %	Certified Average of 25 Alkali % Na ₂ O eq	Standard Deviation
								2 Days (N/mm ²)	7 Days (N/mm ²)	28 Days (N/mm ²)			
15-Jun-26	410	155	0	32.0	50.5		0.04	0.66	0.03				
16-Jun-26	410	160		32.0	51.0		0.04	0.66	0.03				
17-Jun-26	410	155		30.0	50.5		0.04	0.66	0.03				
19-Jun-26	420	165		30.5	49.0		0.04	0.66	0.03				
Average	415	160		31.0	50.5								
26-May-26	410	150	1	29.5	49.0	61.5	0.04	0.64	0.02				
27-May-26	435	155		33.5	51.5	64.5	0.04	0.64	0.03				
28-May-26	425	150		30.5	50.5	64.0	0.05	0.65	0.03				
29-May-26	435	155		31.5	51.5	63.5	0.05	0.65	0.03				
Average	425	155		31.5	50.5	63.5							

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Mean Chloride content (%) = 0.07 (Max)

For and on behalf of
 HEIDELBERG MATERIALS UK

Dr Nina Cardinal, Dipl.Ing., CEng, MICT
 Technical Strategy Director
 Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.