



1333

Heidelberg Materials UK
Second Floor, Arena Court, Crown Lane
Maidenhead, Berkshire, SL6 8QZ
Ribblesdale Works
1333-CPR-00127



Cement Test Report

Heidelberg Materials
UK
Ketton
Stamford
PE9 3SX
Tel: 0330 123 2074
Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of
Ribblesdale PC, BS EN 197-1:2011 - CEM I 52,5N

Dispatched from Ribblesdale during week ending
and during week ending

20-Sep-26 (Week No. 2026-37)
30-Aug-26 (Week No. 2026-34) for 28 day results

Date	Fineness	Setting Time	Soundness	Compressive Strength			Chloride	Alkali	
	Specific Surface (m ² /kg)	Initial (mins)	Expansion (mm)	40mm x 40mm x 160mm Mortar prisms			mean of 25 %	Certified Average of 25 Alkali % Na ₂ O eq	Standard Deviation
				2 Days (N/mm ²)	7 Days (N/mm ²)	28 Days (N/mm ²)			
14-Sep-26	400	135	1	38.5	50.0		0.07	0.69	0.03
15-Sep-26	390	140		37.0	50.0		0.07	0.69	0.03
16-Sep-26	400	145		39.0	51.0		0.07	0.69	0.03
17-Sep-26	400	140		40.0	51.0		0.07	0.68	0.03
18-Sep-26	410	145		41.0	53.5		0.07	0.68	0.03
Average	400	140		39.0	51.0				
24-Aug-26	370	130	0	36.0	49.0	59.0	0.07	0.69	0.03
25-Aug-26	385	135		36.5	47.0	56.0	0.07	0.69	0.03
26-Aug-26	430	135		39.0	49.5	56.5	0.07	0.69	0.03
27-Aug-26	390	130		38.0	49.5	58.5	0.07	0.69	0.03
28-Aug-26	385	125		37.5	50.0	58.5	0.07	0.69	0.03
Average	390	130		37.5	49.0	57.5			

Product Declaration:

Declared Mean Alkali (%) = 0.75 (Max)

Declared Mean Chloride content (%) = 0.07 (Max)

For and on behalf of
HEIDELBERG MATERIALS UK

Dr Nina Cardinal, Dipl.Ing., CEng, MICT
Technical Strategy Director
Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.