Heidelberg Materials UK
Second Floor, Arena Court, Crown Lane
Maidenhead, Berkshire, SL6 8QZ
Ketton Works
1333-CPR-00122

UK CA
1333

Heidelberg Materials

Cement Test Report

Heidelberg Materials
UK
Ketton
Stamford
PE9 3SX
Tel: 0330 123 2074
Fax: 01780 727008

Results of tests made at the laboratories of the company on samples of
Ketton PC, BS EN 197-1:2011 - CEM I 52,5N
Dispatched from Ketton during week ending 25-Oct-26 (Week No. 2026-42)
and during week ending 04-Oct-26 (Week No. 2026-39) for 28 day results

Date	Fineness	Setting Time	Soundness	Compressive Strength			Chloride	Alkali	
	Specific Surface (m^2/kg)	Initial (mins)	Expansion (mm)	40mm x 40mm x 160mm Mortar prisms			mean of 25 %	Certified Average of 25 Alkali % Na_2O eq	Standard Deviation
				2 Days (N/mm^2)	7 Days (N/mm^2)	28 Days (N/mm^2)			
19-Oct-26	430	170	0	31.0	52.0		0.03	0.61	0.04
20-Oct-26	435	160		32.5	53.0		0.03	0.62	0.03
21-Oct-26	420	175		30.0	51.0		0.03	0.62	0.03
23-Oct-26	430	170		31.0	51.5		0.03	0.62	0.03
Average	430	170		31.0	52.0				
28-Sep-26	435	190	1	32.0	52.5	68.5	0.03	0.61	0.03
29-Sep-26	425	195		32.5	51.5	64.5	0.03	0.61	0.03
30-Sep-26	440	195		31.5	51.5	63.0	0.03	0.61	0.03
02-Oct-26	435	200		31.0	49.5	63.5	0.03	0.61	0.03
Average	435	195		32.0	51.5	65.0			

Product Declaration:
Declared Mean Alkali (%) = 0.75 (Max)
Declared Mean Chloride content (%) = 0.07 (Max)

For and on behalf of
HEIDELBERG MATERIALS UK

Dr Nina Cardinal, Dipl.Ing., CEng, MICT
Technical Strategy Director
Heidelberg Materials UK

Heidelberg Materials UK has used all reasonable care to ensure the information herein contained is accurate but to the extent permitted in law, no liability can be accepted by Heidelberg Materials UK for any loss, damage, cost or expense arising from any inaccuracy, whether due to negligence or otherwise.